

Characteristics of Material



冠磁企業股份有限公司
CROWN FERRITE ENTERPRISE CO.
TEL:886-2-2633-1155 FAX:886-2-2633-4214
<http://www.cfe.com.tw> e-mail:crownco@cfec.com.tw

Material L18K

| μ_i | $\tan \delta / \mu_i$ | amr | Bm | Br | Hc | Tc | r | d |
|---------|--------------------------|-----------------------------|-------|-------|---------|------------|---------------|------------|
| - | $\times 10^{-6}$ | $\times 10^{-6} / ^\circ C$ | Gauss | Gauss | Oersted | $^\circ C$ | $\Omega - cm$ | g / cm^3 |
| 1800 | 3(0.01MHz) 40(1.0MHz) | 2 | 3800 | 2500 | 1.1 | 140 | 10^7 | 5.0 |

