

Characteristics of Material



冠磁企業股份有限公司
CROWN FERRITE ENTERPRISE CO.
TEL:886-2-2633-1155 FAX:886-2-2633-4214
http://www.cfe.com.tw e-mail:crownco@cfe.com.tw

Material LI1

μ_i	$\tan \delta / \mu_i$	$\alpha \mu r$	Bm	Br	Hc	Tc	r	d
-	$\times 10^{-6}$	$\times 10^{-6} / ^\circ C$	Gauss	Gauss	Oersted	$^\circ C$	$\Omega - cm$	g / cm^3
750	40(0.1MHz) 400(6.0MHz)	2	3500	2300	0.8	150	10^7	5.0

